

Postal address		Visiting address	
Swerea IVF AB		Argongatan 30, SE- 431 53 MÖLNDAL	
Box 104 SE-431 22 MÖLNDAL		Org. nr. 556053-1526	
Tfn +46 (0)31 706 60 00 Fax +46 (0)31 706 63		VAT no. SE556053-152601	
Client		Client's ref. no.	
Egida Ltd			
Krasnoborskaya 2-ya Str.		Contact person	
420079 Kazan, Tartarstan, RUSSIA		Gulnara Yakhina	
		Our ref. no.	
		5180484-8	

Object

Determination of ash content according to IKEA specification IOS-MAT-0076, version no AA-300587-6.

Test Material

1	Material producer:	Egida Ltd
	Material description:	ST2536 polyurethane foam
	Material batch number or equivalent:	17.05.2018

The test material was received from the client 2018-06-11.

Procedure and results

Ash content was determined according to ISO 1171, modified (end temperature 725°C instead of 900°C, maintained in 60 ±3 min).

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2018-06-13 -- 14

Table 1. Ash content

Test material	Specimen	Sample weight	Ash content
		[g]	[%]
1	1	3.01	0.13
	2	3.12	0.26
	Mean value		0.2


All results relate only to the material tested.

Möln dal, 2018-07-04

Swerea IVF



Desiré Rex
Project leader, Foam Testing



Simonetta Granello
Test Engineer

This report may not be reproduced other than in full, except with prior written approval of the issuing laboratory.
General terms and conditions for Swerea IVF apply and are available on www.swereaivf.se or may be ordered from Swerea IVF.